


Stock Range				
g/m ²	450 x 640	630 x 880	640 x 900	720 x 1020
115	✓	✓	✓	✓
130	✓	✓	✓	✓
150	✓	✓	✓	✓
170	✓		✓	✓
200	✓		✓	✓
220			✓	
250	✓		✓	✓
270			✓	
300	✓		✓	✓
350	✓		✓	✓



Weight	Thickness	Bulk	Brightness	Whiteness	Opacity	Gloss	Smoothness
g/m ²	ISO 534 cm ³ /g	ISO 534 cm ³ /g	ISO 2470-2%	CIE	ISO 2471%	ISO 8254-2%	PPS 10
80*	59	0.74	98	125	90	68	0.8
90*	67	0.74	98	125	91	70	0.8
100	72	0.72	98	125	92	72	0.8
115	85	0.74	98	125	94.5	72	0.8
130	96	0.74	98	125	95	72	0.8
150	111	0.74	98	125	97	72	0.8
170	128	0.75	98	125	97.5	75	0.8
200	148	0.74	98	125	98.5	75	0.8
220	185	0.84	98	125	99	70	0.8
250	184	0.74	98	125	99.5	75	0.8
270	230	0.85	98	125	99.5	70	0.8
300	225	0.75	98	125	99.6	75	0.8
350	272	0.78	98	125	99.8	75	0.8
400*	330	0.85	98	125	99.8	75	1

* Available ex-mill, subject to minimum order quantity

denmaur
papermedia

www.denmaur.com

UPM Finesse gloss