

Weight	Thickness	Bending Resistance			Bending Moment			Bendtsen Roughness	PPS	Cobb Test	Moisture	Colour		
g/m ²	µm	mN			mN.m			mL/min	µm	gHz ₂ /Om ²	%	L	a	b
		I MD	T CD	G GM	I MD	T CD	G GM							
276	393	390	173	260	18.8	8.4	12.6	100	1.5	40	7.5	92.7	0	2.2
285	455	595	262	395	28.7	12.7	19.1	100	1.5	40	7.5	92.7	0	2.2
312	505	825	360	545	39.9	17.4	26.3	100	1.5	40	7.5	92.7	0	2.2
332	540	1000	422	650	48.3	20.4	31.4	100	1.5	40	7.5	92.7	0	2.2
360	600	1050	520	739	50.7	25.1	35.7	100	1.5	40	7.5	92.7	0	2.2
+/- 5%'	+/- 5%'	- 15%'			- 15%'			<300'	<3'	+/- 40%'	+/- 2'	+/- 0.7'	+/- 0.25'	+/- 0.5'
Tolerances														

CERTIFICATIONS



OPTION

High stiffness coated natural kraft board

Suitable for a wide variety of end use packaging products



Multi-ply construction enables a range of finishing applications



Comparatively bulkier with superior rigidity values



Certified for food packaging



Fully Compostable, Biodegradable and Recyclable



Stock Range

	640x900	640x910	720x1020	1020x720
276g/m ² / 393µm	✓		✓	✓
285g/m ² / 455µm	✓	✓	✓	✓
312g/m ² / 505µm	✓		✓	✓
332g/m ² / 540µm	✓		✓	✓
360g/m ² / 600µm	✓		✓	✓

denmaur
papermedia

www.denmaur.com

KlaFold®