



Gloss Stock Range

g/m ²	Sheets						CutStar Reels			
	450 x 640	520 x 720	630 x 880	640 x 900	720 x 1020	900 x 640	1020 x 720	880	900	1020
90	✓		✓	✓	✓			✓		✓
100	✓	✓	✓	✓	✓			✓		✓
115	✓	✓	✓	✓	✓			✓	✓	✓
130	✓	✓	✓	✓	✓			✓	✓	✓
150	✓	✓	✓	✓	✓			✓		✓
170	✓	✓	✓	✓	✓			✓	✓	✓
200	✓	✓		✓	✓				✓	
250	✓	✓		✓	✓	•	•			
300	✓	✓		✓	✓	•	•			
350	✓	✓		✓	✓					

- Short Grain

Gloss Technical Specifications

Weight	g/m ²	90	100	115	130	150	170	200	250	300	350	380*	400*
Thickness	µm	70	76	84	95	108	122	146	188	235	275	310	320
Gloss	ISO 8254-1	71	73	77	78	78	78	78	78	75	75	74	74
Brightness	ISO 2470 %	94.5	94.5	94.5	95	95	95	95	95	95	95	95	95
Opacity	ISO 2471 %	91	93.5	95	96	97	97 min	98 min	98 min	98 min	98 min	98 min	99 min

- * available ex-mill, subject to minimum order quantity



Print Processes

Litho	CutStar	HSWO*	Digital**
✓	✓	✓	✓

* Available ex-mill

** Please see Amadeus Digital swatch

Finishing Suitability

Laminate	Spot UV	Varnish	Foil Block	Folding	Die Cut	Emboss	Scoring
✓	✓	✓	✓	✓	✓	✓	✓

Sustainability

Pulp			Environmental		Quality	H&S
FSC®	ECF	ORIGIN	EU Ecolabel	ISO 14001	ISO 9001	OHSAS 18001
✓	✓	✓	✓	✓	✓	✓

FSC® Forest Stewardship Council® Forest management certification scheme

ECF Elemental Chlorine Free

ORIGIN Identification of tree species used for pulp manufacture obtainable on request

EU Ecolabel European environmental award for overall environmental performance

ISO 14001 International standard for environmental management

ISO 9001 International standard for quality management

OHSAS 18001 International standard for health & safety management

Published 12th April 2019