



FABRIANO

PERGAMON



TECHNICAL SPECIFICATIONS

Pergamon Translucent Ice & Ivory

GSM	Thickness	Roughness	Tensile Strength	
	ISO 534 μm	ISO 8791-2 ml/min	long+/-10%	trasv+/-10%
110	110	450 +/- 100	11.7	4.5
160	160	450 +/- 100	15	7.2
230	230	600 +/- 100	19	9.8

Pergamon Translucent Extra White

GSM	ISO 534 μm	ISO 5627 ml/min	long+/-10%	trasv+/-10%
80	75	25 +/-10	-	-
90	80	25 +/-10	-	-
100	85	25 +/-10	-	-
110	95	25 +/-10	-	-
180	140	13 +/- 5	-	-
200	160	12 +/- 5	-	-
240	185	10 +/- 5	-	-

Pergamon Translucent Premium White

90	80	25 +/-10	-	-
180	140	13 +/- 5	-	-

STOCK RANGE

GSM	700 x 1000
Translucent Ice & Ivory	
110	•
160	•
Translucent Extra White	
80	•
90	•
100	•
110	•
160	•
180	•
200	•
240	•
Translucent Premium White	
90	•
180	•

* 48 hour delivery on this range

FINISHING SUITABILITY

Laminate	Spot UV	Varnish	Foil Block	Folding	Die Cut	Embossing	Scoring
✓	✓	✓	✓	✓	✓	✓	✓

PRINTING PROCESSES

Litho
✓



FABRIANO

PERGAMON



SUSTAINABILITY STATEMENT						
PULP			ENVIRONMENTAL	QUALITY	ENERGY	H&S
FSC	ECF	EUTR	ISO 14001	ISO 9001	ISO 50001	OHSAS 18001
✓	✓	✓	✓			

PRODUCT COMPLIANCE		
EUTR EU (995/2010)	✓	Manufactured in the EU. Full due diligence relating to legal sourcing of timber has been performed
Modern Slavery Act	✓	Supply chain for this product has been fully risk assessed
Pulp Traceability	✓	Full details available on request
REACH	✓	Fulfils requirements - EU (1907/2006) for Registration, Evaluation and Authorisation of Chemicals
Product Safety	✓	Certificate available on request