



Technical Specifications

Weight	g/m ²	54*	57*	60*	65*	70*	80*	90*
Thickness	µm	51.3	54.1	57.0	61.7	66.5	76.0	85.5
Bulk	ISO 534 cm ³ /g	0.95	0.95	0.95	0.95	0.95	0.95	0.95
Brightness	ISO 2470 %	80	82	82	84	84	84	84
Gloss	ISO 8254-1 %	35	35	35	35	35	35	35
Opacity	DIN53146 %	92	92	92	92	92	94	94

* Please note that these weights are available from the mill.

Print Processes

Litho	HSWO	CutStar	Gravure
✓	✓	✓	✓

Finishing Suitability

Laminate	Varnish	Foil Block	Folding	Die Cut	Emboss	Scoring
✓	✓	✓	✓	✓	✓	✓

Sustainability

Pulp		Environmental				Quality	Energy	H&S
FSC®	Recycled	Blue Angel	EU Ecolabel	ISO 14001	EMAS	ISO 9001	ISO 50001	OHSAS 18001
✓	✓	✓	✓	✓	✓	✓	✓	✓

FSC® Forest Stewardship Council® Forest management certification scheme

Blue Angel The ecolabel of the Federal Government of Germany since 1978

EU Ecolabel European environmental award for overall environmental performance

ISO 14001 International standard for environmental management

EMAS Eco-Management and Audit Scheme

ISO 9001 International standard for quality management

ISO 50001 International standard for energy management

OHSAS 18001 International standard for health & safety management

Updated – 12th February 2020 (Please note that this product is ex-mill only – please contact your local Denmaur office for further information)