



revive™ 50 Silk

Stock Range

g/m ²	450 x 640	640 x 900	720 x 1020
115	✓	✓	✓
130	✓	✓	✓
150	✓	✓	✓
170	✓	✓	✓

Technical Specifications

Weight	g/m ²	90*	100*	115	130	150	170	200*	250*	300*	350*
Thickness	µm	73	80	92	104	120	136	165	215	270	325
Bulk	ISO 534 cm ² /g	0.81	0.8	0.8	0.8	0.8	0.8	0.83	0.86	0.9	0.93
Brightness	ISO 2470 %	97	97	97	97	97	97	97	97	97	97
Smoothness	ISO 5627 s	500	500	500	450	450	400	350	350	350	350
Opacity	ISO 2471 %	92.5	94	95	96	97	98	98	98	98	98

* Please note that these weights are available on an ex-mill basis.



revive™ 50 Silk

Print Processes

Litho	Dry Toner Colour Digital*	HSWO **	CutStar **
✓	✓	✓	✓

* Compatible for most dry toner digital presses

** Available on an ex-mill basis

Finishing Suitability

Laminate	Spot UV	Varnish	Foil Block	Folding	Die Cut	Emboss	Scoring
✓	✓	✓	✓	✓	✓	✓	✓

Sustainability

Pulp		Environmental	Quality	Energy
FSC®	Recycled	ISO 14001	ISO 9001	ISO 50001
✓	✓	✓	✓	✓

FSC® Forest Stewardship Council® Forest management certification scheme

ISO 9001 International standard for quality management

ISO 14001 International standard for environmental management

ISO 50001 International standard for energy management

Updated and published : 23rd April 2019