



UPM Finesse gloss



Gloss Stock Range

g/m	450 x 640	520 x 720	630 x 880	640 x 900	720 x 1020
90	✓		✓	✓	✓
100	✓			✓	✓
115	✓		✓	✓	✓
130	✓	✓	✓	✓	✓
150	✓		✓	✓	✓
170	✓			✓	✓
200	✓	✓		✓	✓
220				✓	
250	✓	✓		✓	✓
270	✓			✓	
300	✓	✓		✓	✓
350	✓	✓		✓	✓

Print Processes

Litho	CutStar*	HSWO *
✓	✓	✓

* available on an ex-mill basis

Finishing Suitability

Laminate	Spot UV	Varnish	Foil Block	Folding	Die Cut	Emboss	Scoring
✓	✓	✓	✓	✓	✓	✓	✓



UPM Finesse gloss



Gloss Technical Specifications

Weight	g/m ²	90	100	115	130	150	170	200	220	250	270	300	350
Whiteness	CIE %	125	125	125	125	125	125	125	125	125	125	125	125
Thickness	µm	67	72	85	96	111	128	148	182	184	235	225	270
Bulk	ISO534 cm ³ /g	0.74	0.74	0.74	0.74	0.75	0.75	0.75	0.83	0.75	0.87	0.75	0.77
Brightness	ISO 2470-2 %	98	98	98	98	98	98	98	98	98	98	98	98
Roughness	ISO 8791-4	0.8	0.8	0.8	0.8	0.8	0.8	0.8	0.8	0.8	0.8	0.8	0.8
Opacity	ISO2471%	91	92	94	95	97	97.5	98.3	99	99	99.5	99.6	99.8

Sustainability

Pulp			Environmental			Quality, Health & Safety		
FSC®	ECF	ORIGIN	EMAS	EU Ecolabel	ISO 14001	ISO 9001	ISO 50001	OHSAS 18001
✓	✓	✓	✓	✓	✓	✓	✓	✓

ECF Elemental Chlorine Free

FSC® Forest Stewardship Council® Forest management certification scheme

ORIGIN Identification of tree species used for pulp manufacture obtainable on request

EU Ecolabel European environmental award for overall environmental performance

ISO 14001 International standard for environmental management

ISO 9001 International standard for quality management

ISO 50001 International standard for energy management

OHSAS 18001 International standard for health & safety management

Updated : 22nd February 2019